


Steel Wire Rope 6x36WS-FC

Product information



ISO 4309 Rope Category No: RCN.09

[... Read more](#)




Rope construction: 6x36WS-FC
Marking: According to standard
Standard: EN 12385-4

Fill factor: 0.5
RCN: 09

Slings



Overhead cranes



Steel Wire Rope 6x36WS-FC

Technical data

Part code	Rope diameter	Tensile strength N/mm ²	Finish	Rope lay	Min. breaking force kN	Steel area mm ²	Lubrication	Weight kg/100m
01.B10216080E	8	1,770	Bright	sZ	37.4	25.2	A-1	24
01.B20216080E	8	1,770	Bright	zS	37.4	25.2	A-1	24
01.G10216080E	8	1,770	Galvanized	sZ	37.4	25.2	A-1	24
01.G20216080E	8	1,770	Galvanized	zS	37.4	25.2	A-1	24
01.B10216080G	8	1,960	Bright	sZ	41.4	25.2	A-1	24
01.B20216080G	8	1,960	Bright	zS	41.4	25.2	A-1	24
01.G10216080G	8	1,960	Galvanized	sZ	41.4	25.2	A-1	24
01.G20216080G	8	1,960	Galvanized	zS	41.4	25.2	A-1	24
01.B10216080H	8	2,160	Bright	sZ	45.6	25.2	A-1	24
01.B20216080H	8	2,160	Bright	zS	45.6	25.2	A-1	24
01.G10216080H	8	2,160	Galvanized	sZ	45.6	25.2	A-1	24
01.G20216080H	8	2,160	Galvanized	zS	45.6	25.2	A-1	24
01.B10216090E	9	1,770	Bright	sZ	47.3	31.8	A-1	30
01.B20216090E	9	1,770	Bright	zS	47.3	31.8	A-1	30
01.G10216090E	9	1,770	Galvanized	sZ	47.3	31.8	A-1	30
01.G20216090E	9	1,770	Galvanized	zS	47.3	31.8	A-1	30
01.B10216090G	9	1,960	Bright	sZ	52.4	31.8	A-1	30
01.B20216090G	9	1,960	Bright	zS	52.4	31.8	A-1	30
01.G10216090G	9	1,960	Galvanized	sZ	52.4	31.8	A-1	30
01.G20216090G	9	1,960	Galvanized	zS	52.4	31.8	A-1	30
01.B10216090H	9	2,160	Bright	sZ	57.7	31.8	A-1	30
01.B20216090H	9	2,160	Bright	zS	57.7	31.8	A-1	30
01.G10216090H	9	2,160	Galvanized	sZ	57.7	31.8	A-1	30
01.G20216090H	9	2,160	Galvanized	zS	57.7	31.8	A-1	30
01.B10216100E	10	1,770	Bright	sZ	58.4	39.3	A-1	37
01.B20216100E	10	1,770	Bright	zS	58.4	39.3	A-1	37
01.G10216100E	10	1,770	Galvanized	sZ	58.4	39.3	A-1	37
01.G20216100E	10	1,770	Galvanized	zS	58.4	39.3	A-1	37
01.B10216100G	10	1,960	Bright	sZ	64.7	39.3	A-1	37
01.B20216100G	10	1,960	Bright	zS	64.7	39.3	A-1	37
01.G10216100G	10	1,960	Galvanized	sZ	64.7	39.3	A-1	37

Steel Wire Rope 6x36WS-FC

Technical data

Part code	Rope diameter	Tensile strength N/mm ²	Finish	Rope lay	Min. breaking force kN	Steel area mm ²	Lubrication	Weight kg/100m
01.G20216100G	10	1,960	Galvanized	zS	64.7	39.3	A-1	37
01.B10216100H	10	2,160	Bright	sZ	71.3	39.3	A-1	37
01.B20216100H	10	2,160	Bright	zS	71.3	39.3	A-1	37
01.G10216100H	10	2,160	Galvanized	sZ	71.3	39.3	A-1	37
01.G20216100H	10	2,160	Galvanized	zS	71.3	39.3	A-1	37
01.B10216110E	11	1,770	Bright	sZ	70.7	47.6	A-1	44
01.B20216110E	11	1,770	Bright	zS	70.7	47.6	A-1	44
01.G10216110E	11	1,770	Galvanized	sZ	70.7	47.6	A-1	44
01.G20216110E	11	1,770	Galvanized	zS	70.7	47.6	A-1	44
01.B10216110G	11	1,960	Bright	sZ	78.3	47.6	A-1	44
01.B20216110G	11	1,960	Bright	zS	78.3	47.6	A-1	44
01.G10216110G	11	1,960	Galvanized	sZ	78.3	47.6	A-1	44
01.G20216110G	11	1,960	Galvanized	zS	78.3	47.6	A-1	44
01.B10216110H	11	2,160	Bright	sZ	86.2	47.6	A-1	44
01.B20216110H	11	2,160	Bright	zS	86.2	47.6	A-1	44
01.G10216110H	11	2,160	Galvanized	sZ	86.2	47.6	A-1	44
01.G20216110H	11	2,160	Galvanized	zS	86.2	47.6	A-1	44
01.B10216120E	12	1,770	Bright	sZ	84.1	56.6	A-1	53
01.B20216120E	12	1,770	Bright	zS	84.1	56.6	A-1	53
01.G10216120E	12	1,770	Galvanized	sZ	84.1	56.6	A-1	53
01.G20216120E	12	1,770	Galvanized	zS	84.1	56.6	A-1	53
01.B10216120G	12	1,960	Bright	sZ	93.1	56.6	A-1	53
01.B20216120G	12	1,960	Bright	zS	93.1	56.6	A-1	53
01.G10216120G	12	1,960	Galvanized	sZ	93.1	56.6	A-1	53
01.G20216120G	12	1,960	Galvanized	zS	93.1	56.6	A-1	53
01.B10216120H	12	2,160	Bright	sZ	103	56.6	A-1	53
01.B20216120H	12	2,160	Bright	zS	103	56.6	A-1	53
01.G10216120H	12	2,160	Galvanized	sZ	103	56.6	A-1	53
01.G20216120H	12	2,160	Galvanized	zS	103	56.6	A-1	53
01.B10216130E	13	1,770	Bright	sZ	98.7	66.4	A-1	62
01.B20216130E	13	1,770	Bright	zS	98.7	66.4	A-1	62

Steel Wire Rope 6x36WS-FC

Technical data

Part code	Rope diameter	Tensile strength N/mm ²	Finish	Rope lay	Min. breaking force kN	Steel area mm ²	Lubrication	Weight kg/100m
01.G10216130E	13	1,770	Galvanized	sZ	98.7	66.4	A-1	62
01.G20216130E	13	1,770	Galvanized	zS	98.7	66.4	A-1	62
01.B10216130G	13	1,960	Bright	sZ	109	66.4	A-1	62
01.B20216130G	13	1,960	Bright	zS	109	66.4	A-1	62
01.G10216130G	13	1,960	Galvanized	sZ	109	66.4	A-1	62
01.G20216130G	13	1,960	Galvanized	zS	109	66.4	A-1	62
01.B10216130H	13	2,160	Bright	sZ	120	66.4	A-1	62
01.B20216130H	13	2,160	Bright	zS	120	66.4	A-1	62
01.G10216130H	13	2,160	Galvanized	sZ	120	66.4	A-1	62
01.G20216130H	13	2,160	Galvanized	zS	120	66.4	A-1	62
01.B10216140E	14	1,770	Bright	sZ	114	77	A-1	72
01.B20216140E	14	1,770	Bright	zS	114	77	A-1	72
01.G10216140E	14	1,770	Galvanized	sZ	114	77	A-1	72
01.G20216140E	14	1,770	Galvanized	zS	114	77	A-1	72
01.B10216140G	14	1,960	Bright	sZ	127	77	A-1	72
01.B20216140G	14	1,960	Bright	zS	127	77	A-1	72
01.G10216140G	14	1,960	Galvanized	sZ	127	77	A-1	72
01.G20216140G	14	1,960	Galvanized	zS	127	77	A-1	72
01.B10216140H	14	2,160	Bright	sZ	140	77	A-1	72
01.B20216140H	14	2,160	Bright	zS	140	77	A-1	72
01.G10216140H	14	2,160	Galvanized	sZ	140	77	A-1	72
01.G20216140H	14	2,160	Galvanized	zS	140	77	A-1	72
01.B10216160E	16	1,770	Bright	sZ	150	101	A-1	94
01.B20216160E	16	1,770	Bright	zS	150	101	A-1	94
01.G10216160E	16	1,770	Galvanized	sZ	150	101	A-1	94
01.G20216160E	16	1,770	Galvanized	zS	150	101	A-1	94
01.B10216160G	16	1,960	Bright	sZ	166	101	A-1	94
01.B20216160G	16	1,960	Bright	zS	166	101	A-1	94
01.G10216160G	16	1,960	Galvanized	sZ	166	101	A-1	94
01.G20216160G	16	1,960	Galvanized	zS	166	101	A-1	94
01.B10216160H	16	2,160	Bright	sZ	182	101	A-1	94

Steel Wire Rope 6x36WS-FC

Technical data

Part code	Rope diameter	Tensile strength N/mm ²	Finish	Rope lay	Min. breaking force kN	Steel area mm ²	Lubrication	Weight kg/100m
01.B20216160H	16	2,160	Bright	zS	182	101	A-1	94
01.G10216160H	16	2,160	Galvanized	sZ	182	101	A-1	94
01.G20216160H	16	2,160	Galvanized	zS	182	101	A-1	94
01.B10216180E	18	1,770	Bright	sZ	189	127	A-1	119
01.B20216180E	18	1,770	Bright	zS	189	127	A-1	119
01.G10216180E	18	1,770	Galvanized	sZ	189	127	A-1	119
01.G20216180E	18	1,770	Galvanized	zS	189	127	A-1	119
01.B10216180G	18	1,960	Bright	sZ	210	127	A-1	119
01.B20216180G	18	1,960	Bright	zS	210	127	A-1	119
01.G10216180G	18	1,960	Galvanized	sZ	210	127	A-1	119
01.G20216180G	18	1,960	Galvanized	zS	210	127	A-1	119
01.B10216180H	18	2,160	Bright	sZ	231	127	A-1	119
01.B20216180H	18	2,160	Bright	zS	231	127	A-1	119
01.G10216180H	18	2,160	Galvanized	sZ	231	127	A-1	119
01.G20216180H	18	2,160	Galvanized	zS	231	127	A-1	119
01.B10216190E	19	1,770	Bright	sZ	211	142	A-1	132
01.B20216190E	19	1,770	Bright	zS	211	142	A-1	132
01.G10216190E	19	1,770	Galvanized	sZ	211	142	A-1	132
01.G20216190E	19	1,770	Galvanized	zS	211	142	A-1	132
01.B10216190G	19	1,960	Bright	sZ	233	142	A-1	132
01.B20216190G	19	1,960	Bright	zS	233	142	A-1	132
01.G10216190G	19	1,960	Galvanized	sZ	233	142	A-1	132
01.G20216190G	19	1,960	Galvanized	zS	233	142	A-1	132
01.B10216190H	19	2,160	Bright	sZ	257	142	A-1	132
01.B20216190H	19	2,160	Bright	zS	257	142	A-1	132
01.G10216190H	19	2,160	Galvanized	sZ	257	142	A-1	132
01.G20216190H	19	2,160	Galvanized	zS	257	142	A-1	132
01.B10216200E	20	1,770	Bright	sZ	234	157	A-1	147
01.B20216200E	20	1,770	Bright	zS	234	157	A-1	147
01.G10216200E	20	1,770	Galvanized	sZ	234	157	A-1	147
01.G20216200E	20	1,770	Galvanized	zS	234	157	A-1	147

Steel Wire Rope 6x36WS-FC

Technical data

Part code	Rope diameter	Tensile strength N/mm ²	Finish	Rope lay	Min. breaking force kN	Steel area mm ²	Lubrication	Weight kg/100m
01.B10216200G	20	1,960	Bright	sZ	259	157	A-1	147
01.B20216200G	20	1,960	Bright	zS	259	157	A-1	147
01.G10216200G	20	1,960	Galvanized	sZ	259	157	A-1	147
01.G20216200G	20	1,960	Galvanized	zS	259	157	A-1	147
01.B10216200H	20	2,160	Bright	sZ	285	157	A-1	147
01.B20216200H	20	2,160	Bright	zS	285	157	A-1	147
01.G10216200H	20	2,160	Galvanized	sZ	285	157	A-1	147
01.G20216200H	20	2,160	Galvanized	zS	285	157	A-1	147
01.B10216220E	22	1,770	Bright	sZ	283	190	A-1	178
01.B20216220E	22	1,770	Bright	zS	283	190	A-1	178
01.G10216220E	22	1,770	Galvanized	sZ	283	190	A-1	178
01.G20216220E	22	1,770	Galvanized	zS	283	190	A-1	178
01.B10216220G	22	1,960	Bright	sZ	313	190	A-1	178
01.B20216220G	22	1,960	Bright	zS	313	190	A-1	178
01.G10216220G	22	1,960	Galvanized	sZ	313	190	A-1	178
01.G20216220G	22	1,960	Galvanized	zS	313	190	A-1	178
01.B10216220H	22	2,160	Bright	sZ	345	190	A-1	178
01.B20216220H	22	2,160	Bright	zS	345	190	A-1	178
01.G10216220H	22	2,160	Galvanized	sZ	345	190	A-1	178
01.G20216220H	22	2,160	Galvanized	zS	345	190	A-1	178
01.B10216240E	24	1,770	Bright	sZ	336	226	A-1	211
01.B20216240E	24	1,770	Bright	zS	336	226	A-1	211
01.G10216240E	24	1,770	Galvanized	sZ	336	226	A-1	211
01.G20216240E	24	1,770	Galvanized	zS	336	226	A-1	211
01.B10216240G	24	1,960	Bright	sZ	373	226	A-1	211
01.B20216240G	24	1,960	Bright	zS	373	226	A-1	211
01.G10216240G	24	1,960	Galvanized	sZ	373	226	A-1	211
01.G20216240G	24	1,960	Galvanized	zS	373	226	A-1	211
01.B10216240H	24	2,160	Bright	sZ	411	226	A-1	211
01.B20216240H	24	2,160	Bright	zS	411	226	A-1	211
01.G10216240H	24	2,160	Galvanized	sZ	411	226	A-1	211

Steel Wire Rope 6x36WS-FC

Technical data

Part code	Rope diameter	Tensile strength N/mm ²	Finish	Rope lay	Min. breaking force kN	Steel area mm ²	Lubrication	Weight kg/100m
01.G20216240H	24	2,160	Galvanized	zS	411	226	A-1	211
01.B10216260E	26	1,770	Bright	sZ	395	266	A-1	248
01.B20216260E	26	1,770	Bright	zS	395	266	A-1	248
01.G10216260E	26	1,770	Galvanized	sZ	395	266	A-1	248
01.G20216260E	26	1,770	Galvanized	zS	395	266	A-1	248
01.B10216260G	26	1,960	Bright	sZ	437	266	A-1	248
01.B20216260G	26	1,960	Bright	zS	437	266	A-1	248
01.G10216260G	26	1,960	Galvanized	sZ	437	266	A-1	248
01.G20216260G	26	1,960	Galvanized	zS	437	266	A-1	248
01.B10216260H	26	2,160	Bright	sZ	482	266	A-1	248
01.B20216260H	26	2,160	Bright	zS	482	266	A-1	248
01.G10216260H	26	2,160	Galvanized	sZ	482	266	A-1	248
01.G20216260H	26	2,160	Galvanized	zS	482	266	A-1	248
01.B10216280E	28	1,770	Bright	sZ	458	308	A-1	288
01.B20216280E	28	1,770	Bright	zS	458	308	A-1	288
01.G10216280E	28	1,770	Galvanized	sZ	458	308	A-1	288
01.G20216280E	28	1,770	Galvanized	zS	458	308	A-1	288
01.B10216280G	28	1,960	Bright	sZ	507	308	A-1	288
01.B20216280G	28	1,960	Bright	zS	507	308	A-1	288
01.G10216280G	28	1,960	Galvanized	sZ	507	308	A-1	288
01.G20216280G	28	1,960	Galvanized	zS	507	308	A-1	288
01.B10216280H	28	2,160	Bright	sZ	559	308	A-1	288
01.B20216280H	28	2,160	Bright	zS	559	308	A-1	288
01.G10216280H	28	2,160	Galvanized	sZ	559	308	A-1	288
01.G20216280H	28	2,160	Galvanized	zS	559	308	A-1	288
01.B10216300E	30	1,770	Bright	sZ	526	354	A-1	330
01.B20216300E	30	1,770	Bright	zS	526	354	A-1	330
01.G10216300E	30	1,770	Galvanized	sZ	526	354	A-1	330
01.G20216300E	30	1,770	Galvanized	zS	526	354	A-1	330
01.B10216300G	30	1,960	Bright	sZ	582	354	A-1	330
01.B20216300G	30	1,960	Bright	zS	582	354	A-1	330

Steel Wire Rope 6x36WS-FC

Technical data

Part code	Rope diameter	Tensile strength N/mm ²	Finish	Rope lay	Min. breaking force kN	Steel area mm ²	Lubrication	Weight kg/100m
01.G10216300G	30	1,960	Galvanized	sZ	582	354	A-1	330
01.G20216300G	30	1,960	Galvanized	zS	582	354	A-1	330
01.B10216300H	30	2,160	Bright	sZ	642	354	A-1	330
01.B20216300H	30	2,160	Bright	zS	642	354	A-1	330
01.G10216300H	30	2,160	Galvanized	sZ	642	354	A-1	330
01.G20216300H	30	2,160	Galvanized	zS	642	354	A-1	330
01.B10216320E	32	1,770	Bright	sZ	598	402	A-1	376
01.B20216320E	32	1,770	Bright	zS	598	402	A-1	376
01.G10216320E	32	1,770	Galvanized	sZ	598	402	A-1	376
01.G20216320E	32	1,770	Galvanized	zS	598	402	A-1	376
01.B10216320G	32	1,960	Bright	sZ	662	402	A-1	376
01.B20216320G	32	1,960	Bright	zS	662	402	A-1	376
01.G10216320G	32	1,960	Galvanized	sZ	662	402	A-1	376
01.G20216320G	32	1,960	Galvanized	zS	662	402	A-1	376
01.B10216320H	32	2,160	Bright	sZ	730	402	A-1	376
01.B20216320H	32	2,160	Bright	zS	730	402	A-1	376
01.G10216320H	32	2,160	Galvanized	sZ	730	402	A-1	376
01.G20216320H	32	2,160	Galvanized	zS	730	402	A-1	376
01.B10216360E	36	1,770	Bright	sZ	757	509	A-1	476
01.B20216360E	36	1,770	Bright	zS	757	509	A-1	476
01.G10216360E	36	1,770	Galvanized	sZ	757	509	A-1	476
01.G20216360E	36	1,770	Galvanized	zS	757	509	A-1	476
01.B10216360G	36	1,960	Bright	sZ	838	509	A-1	476
01.B20216360G	36	1,960	Bright	zS	838	509	A-1	476
01.G10216360G	36	1,960	Galvanized	sZ	838	509	A-1	476
01.G20216360G	36	1,960	Galvanized	zS	838	509	A-1	476
01.B10216360H	36	2,160	Bright	sZ	924	509	A-1	476
01.B20216360H	36	2,160	Bright	zS	924	509	A-1	476
01.G10216360H	36	2,160	Galvanized	sZ	924	509	A-1	476
01.G20216360H	36	2,160	Galvanized	zS	924	509	A-1	476
01.B10216380E	38	1,770	Bright	sZ	843	567	A-1	530

Steel Wire Rope 6x36WS-FC

Technical data

Part code	Rope diameter	Tensile strength N/mm ²	Finish	Rope lay	Min. breaking force kN	Steel area mm ²	Lubrication	Weight kg/100m
01.B20216380E	38	1,770	Bright	zS	843	567	A-1	530
01.G10216380E	38	1,770	Galvanized	sZ	843	567	A-1	530
01.G20216380E	38	1,770	Galvanized	zS	843	567	A-1	530
01.B10216380G	38	1,960	Bright	sZ	934	567	A-1	530
01.B20216380G	38	1,960	Bright	zS	934	567	A-1	530
01.G10216380G	38	1,960	Galvanized	sZ	934	567	A-1	530
01.G20216380G	38	1,960	Galvanized	zS	934	567	A-1	530
01.B10216380H	38	2,160	Bright	sZ	1,029	567	A-1	530
01.B20216380H	38	2,160	Bright	zS	1,029	567	A-1	530
01.G10216380H	38	2,160	Galvanized	sZ	1,029	567	A-1	530
01.G20216380H	38	2,160	Galvanized	zS	1,029	567	A-1	530
01.B10216400E	40	1,770	Bright	sZ	935	629	A-1	587
01.B20216400E	40	1,770	Bright	zS	935	629	A-1	587
01.G10216400E	40	1,770	Galvanized	sZ	935	629	A-1	587
01.G20216400E	40	1,770	Galvanized	zS	935	629	A-1	587
01.B10216400G	40	1,960	Bright	sZ	1,035	629	A-1	587
01.B20216400G	40	1,960	Bright	zS	1,035	629	A-1	587
01.G10216400G	40	1,960	Galvanized	sZ	1,035	629	A-1	587
01.G20216400G	40	1,960	Galvanized	zS	1,035	629	A-1	587
01.B10216400H	40	2,160	Bright	sZ	1,140	629	A-1	587
01.B20216400H	40	2,160	Bright	zS	1,140	629	A-1	587
01.G10216400H	40	2,160	Galvanized	sZ	1,140	629	A-1	587
01.G20216400H	40	2,160	Galvanized	zS	1,140	629	A-1	587
01.B10216420E	42	1,770	Bright	sZ	1,030	693	A-1	647
01.B20216420E	42	1,770	Bright	zS	1,030	693	A-1	647
01.G10216420E	42	1,770	Galvanized	sZ	1,030	693	A-1	647
01.G20216420E	42	1,770	Galvanized	zS	1,030	693	A-1	647
01.B10216420G	42	1,960	Bright	sZ	1,141	693	A-1	647
01.B20216420G	42	1,960	Bright	zS	1,141	693	A-1	647
01.G10216420G	42	1,960	Galvanized	sZ	1,141	693	A-1	647
01.G20216420G	42	1,960	Galvanized	zS	1,141	693	A-1	647

Steel Wire Rope 6x36WS-FC

Technical data

Part code	Rope diameter	Tensile strength N/mm ²	Finish	Rope lay	Min. breaking force kN	Steel area mm ²	Lubrication	Weight kg/100m
01.B10216420H	42	2,160	Bright	sZ	1,257	693	A-1	647
01.B20216420H	42	2,160	Bright	zS	1,257	693	A-1	647
01.G10216420H	42	2,160	Galvanized	sZ	1,257	693	A-1	647
01.G20216420H	42	2,160	Galvanized	zS	1,257	693	A-1	647
01.B10216440E	44	1,770	Bright	sZ	1,130	761	A-1	711
01.B20216440E	44	1,770	Bright	zS	1,130	761	A-1	711
01.G10216440E	44	1,770	Galvanized	sZ	1,130	761	A-1	711
01.G20216440E	44	1,770	Galvanized	zS	1,130	761	A-1	711
01.B10216440G	44	1,960	Bright	sZ	1,252	761	A-1	711
01.B20216440G	44	1,960	Bright	zS	1,252	761	A-1	711
01.G10216440G	44	1,960	Galvanized	sZ	1,252	761	A-1	711
01.G20216440G	44	1,960	Galvanized	zS	1,252	761	A-1	711
01.B10216440H	44	2,160	Bright	sZ	1,380	761	A-1	711
01.B20216440H	44	2,160	Bright	zS	1,380	761	A-1	711
01.G10216440H	44	2,160	Galvanized	sZ	1,380	761	A-1	711
01.G20216440H	44	2,160	Galvanized	zS	1,380	761	A-1	711
01.B10216480E	48	1,770	Bright	sZ	1,350	905	A-1	846
01.B20216480E	48	1,770	Bright	zS	1,350	905	A-1	846
01.G10216480E	48	1,770	Galvanized	sZ	1,350	905	A-1	846
01.G20216480E	48	1,770	Galvanized	zS	1,350	905	A-1	846
01.B10216480G	48	1,960	Bright	sZ	1,490	905	A-1	846
01.B20216480G	48	1,960	Bright	zS	1,490	905	A-1	846
01.G10216480G	48	1,960	Galvanized	sZ	1,490	905	A-1	846
01.G20216480G	48	1,960	Galvanized	zS	1,490	905	A-1	846
01.B10216480H	48	2,160	Bright	sZ	1,642	905	A-1	846
01.B20216480H	48	2,160	Bright	zS	1,642	905	A-1	846
01.G10216480H	48	2,160	Galvanized	sZ	1,642	905	A-1	846
01.G20216480H	48	2,160	Galvanized	zS	1,642	905	A-1	846
01.B10216520E	52	1,770	Bright	sZ	1,580	1,063	A-1	992
01.B20216520E	52	1,770	Bright	zS	1,580	1,063	A-1	992
01.G10216520E	52	1,770	Galvanized	sZ	1,580	1,063	A-1	992

Steel Wire Rope 6x36WS-FC

Technical data

Part code	Rope diameter	Tensile strength N/mm ²	Finish	Rope lay	Min. breaking force kN	Steel area mm ²	Lubrication	Weight kg/100m
01.G20216520E	52	1,770	Galvanized	zS	1,580	1,063	A-1	992
01.B10216520G	52	1,960	Bright	sZ	1,749	1,063	A-1	992
01.B20216520G	52	1,960	Bright	zS	1,749	1,063	A-1	992
01.G10216520G	52	1,960	Galvanized	sZ	1,749	1,063	A-1	992
01.G20216520G	52	1,960	Galvanized	zS	1,749	1,063	A-1	992
01.B10216520H	52	2,160	Bright	sZ	1,927	1,063	A-1	992
01.B20216520H	52	2,160	Bright	zS	1,927	1,063	A-1	992
01.G10216520H	52	2,160	Galvanized	sZ	1,927	1,063	A-1	992
01.G20216520H	52	2,160	Galvanized	zS	1,927	1,063	A-1	992
01.B10216560E	56	1,770	Bright	sZ	1,830	1,232	A-1	1,151
01.B20216560E	56	1,770	Bright	zS	1,830	1,232	A-1	1,151
01.G10216560E	56	1,770	Galvanized	sZ	1,830	1,232	A-1	1,151
01.G20216560E	56	1,770	Galvanized	zS	1,830	1,232	A-1	1,151
01.B10216560G	56	1,960	Bright	sZ	2,028	1,232	A-1	1,151
01.B20216560G	56	1,960	Bright	zS	2,028	1,232	A-1	1,151
01.G10216560G	56	1,960	Galvanized	sZ	2,028	1,232	A-1	1,151
01.G20216560G	56	1,960	Galvanized	zS	2,028	1,232	A-1	1,151
01.B10216560H	56	2,160	Bright	sZ	2,235	1,232	A-1	1,151
01.B20216560H	56	2,160	Bright	zS	2,235	1,232	A-1	1,151
01.G10216560H	56	2,160	Galvanized	sZ	2,235	1,232	A-1	1,151
01.G20216560H	56	2,160	Galvanized	zS	2,235	1,232	A-1	1,151
01.B10216600E	60	1,770	Bright	sZ	2,100	1,415	A-1	1,321
01.B20216600E	60	1,770	Bright	zS	2,100	1,415	A-1	1,321
01.G10216600E	60	1,770	Galvanized	sZ	2,100	1,415	A-1	1,321
01.G20216600E	60	1,770	Galvanized	zS	2,100	1,415	A-1	1,321
01.B10216600G	60	1,960	Bright	sZ	2,328	1,415	A-1	1,321
01.B20216600G	60	1,960	Bright	zS	2,328	1,415	A-1	1,321
01.G10216600G	60	1,960	Galvanized	sZ	2,328	1,415	A-1	1,321
01.G20216600G	60	1,960	Galvanized	zS	2,328	1,415	A-1	1,321
01.B10216600H	60	2,160	Bright	sZ	2,566	1,415	A-1	1,321
01.B20216600H	60	2,160	Bright	zS	2,566	1,415	A-1	1,321

Steel Wire Rope 6x36WS-FC

Technical data

Part code	Rope diameter	Tensile strength N/mm ²	Finish	Rope lay	Min. breaking force kN	Steel area mm ²	Lubrication	Weight kg/100m
01.G10216600H	60	2,160	Galvanized	sZ	2,566	1,415	A-1	1,321
01.G20216600H	60	2,160	Galvanized	zS	2,566	1,415	A-1	1,321