
MENNENS | Lifting Solutions Group
Axel Johnson International

Steel Wire Rope 6x12-7FC

Product information

sZ G



... Read more

Rope construction: 6x12-7FC

Fill factor: 0.30

Mennens Belgium
sales@mennensbelgium.be
+32 (0)3 253 23 23

© November 2026 - All Rights Reserved

MENNENS | Lifting Solutions Group
Axel Johnson International

Steel Wire Rope 6x12-7FC

Technical data

Part code	Rope diameter mm	Tensile strength N/mm²	Finish	Rope lay	Min. breaking force kN	Steel area mm²	Lubrication	Weight kg/100m
101100304250270	3	1,770	Galvanized	sZ	3.33	2.09	Dry	2.1
101100404250270	4	1,770	Galvanized	sZ	5.92	3.71	Dry	3.7
101100504250270	5	1,770	Galvanized	sZ	9.25	5.8	Dry	5.8
101100604250270	6	1,770	Galvanized	sZ	13.3	8.35	Dry	8.3
101100704250270	7	1,770	Galvanized	sZ	18.1	11.4	Dry	11
101100804250270	8	1,770	Galvanized	sZ	23.7	14.8	Dry	15
101101004250270	10	1,770	Galvanized	sZ	37	23.2	Dry	23
101101204250270	12	1,770	Galvanized	sZ	53.3	33.4	Dry	33

Mennens Belgium
sales@mennensbelgium.be
+32 (0)3 253 23 23

© November 2026 - All Rights Reserved